



External Fabrics  
Collection

VEOZIP

	Technical properties	Standards
Openess factor	5%	
Weight	66 g/m <sup>2</sup>	EN ISO 2286-2
Thickness	0,99 mm	
Width	290 -320 cm	
	Physical properties	
Breaking resistance	250 / 170 daN / 5 cm	EN ISO 1421
Tear resistance	25 / 25 daN	DIN 53363
	Reaction to fire	
Rating	<b>M1</b> /NFP 92-507 — <b>B1</b> /DIN 4102-1 — BS 7837 — BS 5867 — <b>CUNO</b> /UNI 91-77 — <b>Classe 1</b> /EN 13773 — <b>Method 1</b> /NFPA 701 — CSFM T19 — <b>Class A</b> /ASTM E84	
Euroclass	B-s2,d0	EN 13501-1

Quoted technical characteristics are average values subject to +/- 5% tolerance.

The purchaser of our products is responsible for their application or transformation in relation to possible third party rights. Moreover, the purchaser of our products is responsible for their installation and usage in compliance with the standards, working practices and safety regulations of their destination country. Please refer to our warranty document with regard to contractual liability.

Values quoted in this document are commonly used test results for design purposes. They are given for information only in order to offer our customers optimum usage of our products. Our products are subject to improvements resulting from technical developments and we reserve the right to modify their characteristics at any time. The purchaser of our products is responsible for checking the above data

		TS	RS	AS	TV n-h	$g_{tot}^e$ EN13363-2 Type C glazing	$g_{tot}^e$ EN13363-2 Type D glazing
51184	Soltis VeoZip Frost White	9	59	32	8	0,07	0,04
51185	Soltis VeoZip Edelweiss *	9	50	41	8	0,07	0,04
51186	Soltis VeoZip Cumulus	6	37	57	6	0,06	0,04
51187	Soltis VeoZip Natural *	7	37	56	7	0,06	0,04
51188	Soltis VeoZip Macadamia *	5	29	66	4	0,05	0,03
51192	Soltis VeoZip Sea Lion	8	13	79	7	0,07	0,05
51194	Soltis VeoZip Shadow	5	7	88	5	0,06	0,04
51195	Soltis VeoZip Volcano *	5	7	88	5	0,05	0,04
51197	Soltis VeoZip Grey Pepper *	5	8	87	5	0,05	0,04
51198	Soltis VeoZip Graphite Black	5	5	90	5	0,06	0,04

\* Orders might require longer production time. Please contact your sales representative for availability information.

[www.nerligruppen.com](http://www.nerligruppen.com)

ver 2.2

